

## 30% Glass-reinforced high-flow injection moulding grade

### POKETONE Polymer M33FG6B

POKETONE Thermoplastic Polymers are aliphatic polyketones, a revolutionary new class of semi-crystalline thermoplastics. Hyosung developed new catalyst to produce this unique polymer in 2013 and constructed commercial plant in 2015, in Ulsan, Korea.

POKETONE Polymer M33FG6B is a 30 percent short glass-fiber-reinforced high-flow injection moulding grade with mechanical properties that classify it as an engineering thermoplastic. This grade shows a unique balance of toughness and high modulus combined with good creep performance, strength and elevated temperature performance.

This grade exhibits very good processability, good impact resistance, high resilience and good creep performance. POKETONE Polymer M33FG6B can also withstand short-term exposure to elevated temperatures. Moreover this polymer exhibits high resistance to hydrocarbons, solvents, salt solutions, weak acids and weak bases.

POKETONE Polymer M33FG6B is a high-flow, low-viscosity polymer that should be considered for mouldings with long flow paths or thin walls. This grade is very easy to process on standard injection moulding equipment. Cycle times are generally short and parts show good mould definition. POKETONE Polymer's low moisture sensitivity means that no conditioning of parts before assembly or use is necessary.

Applications for POKETONE Polymer M33FG6B may be found in the automotive, electrical, electronics, industrial and consumer appliance markets.

TABLE 1 : TYPICAL MECHANICAL PROPERTIES OF POKETONE POLYMER M33FG6B – Measured at 23 °C				
	Test Method & Conditions		ASTM Values	ISO Values
	ASTM	ISO	SI	SI
Tensile strength at yield	D638	527-1	140 MPa	140 MPa
Tensile modulus	D638	527-1	7,700 MPa	7,500 MPa
Tensile elongation at break	D638	527-1	3.8 %	3.8 %
Flexural strength	D790	178	190 MPa	185 MPa
Flexural modulus	D790	178	6,700 MPa	6,150 MPa
Unnotched Izod impact	D256	180/U	-	104 kJ/m <sup>2</sup>
Notched Izod impact strength	D256	180/A	120 J/m	13 kJ/m <sup>2</sup>
Unnotched Charpy impact strength	-	179/1eU	-	N.B
Notched Charpy Impact strength	-	179/1eA	-	13 kJ/m <sup>2</sup>

TABLE 2: TYPICAL PHYSICAL PROPERTIES OF POKETONE POLYMER M33FG6B – Measured at 23 °C				
	Test Method & Conditions		ASTM Values	ISO Values
	ASTM	ISO	SI	SI
Specific gravity	D792	1183	1.47 g/cm <sup>3</sup>	1.47 g/cm <sup>3</sup>
Shore D hardness	D2240	868	-	83
Hardness Rockwell	D785	-	113	-
Water absorption equilibrium at 50% RH	D570	62	0.4 %	0.4 %
Water absorption at saturation	D570	62	1.7 %	1.7 %

TABLE 3: TYPICAL THERMAL PROPERTIES OF POKETONE POLYMER M33FG6B				
	Test Method & Conditions		ASTM Values	ISO Values
	ASTM	ISO	SI	SI
Melting temperature	D3418	11357	222 °C	222 °C
Coefficient of linear thermal expansion, 25°C to 55°C	E831 TD MD	-	9.7*10 <sup>-5</sup> 2.8*10 <sup>-5</sup>	-
Vicat softening point	D1525 5 kg	306/B50 50N	210°C	210°C
Heat deflection temperature	D648	75	215°C	215°C
	66psi 264psi	0.45 MPa 1.8 MPa	210°C	210°C

TABLE 4: TYPICAL PROCESS RELATED PROPERTIES  
OF POKETONE POLYMER M33FG6B

	Test Method & Conditions		ASTM Values	ISO Values
	ASTM	ISO	SI	SI
Melt flow index 240°C/2.16kg	D1238	1133	14 g/10 min	13ml/10min
Mould shrinkage	D955			
	MD, 3mm		0.2%	
	TD, 3mm	-	1.1%	-
	MD, 2mm		0.1%	
	TD, 2mm		0.9%	


TABLE 5: TYPICAL ELECTRICAL PROPERTIES  
OF POKETONE POLYMER M33FG6B

	Test Method & Conditions	ASTM Values
	ASTM	SI
Dielectric strength, Short term	D149	
	3 mm	17 kV/mm
	2 mm	22 kV/mm
Volume resistivity	D257	10 <sup>14</sup> ohm cm
Surface resistivity	D257	10 <sup>17</sup> ohm/sq.
Dielectric constant at 60Hz	D150	6.3
Dissipation factor at 60Hz	D150	0.011

\*POKETONE is a Hyosung Chemical Corporation Trademark

All products purchased from or supplied by Hyosung Chemical Corporation are subject to terms and conditions set out in the contract, order acknowledgement and/or bill of loading. Hyosung warrants only that its product will meet those specifications designated as such herein or in other publications. All other information, including that herein, supplied by Hyosung is considered accurate but is furnished upon the express condition that the customer shall make its own assessment to determine the product's suitability for a particular purpose. Hyosung makes no other warranty, either express or implied, including those regarding such other information, the data upon which the same is based, or the results to be obtained from the use thereof; that any product shall be merchantable or fit for any particular purpose; or that the use of such other information or product will not infringe any patent. Any references in this brochure to "Hyosung" refer to the collectivity of Hyosung engaged in the manufacture and sale of chemical products. Particular contracts are entered into by any such company individually and any warranty, representation or any other commitment provided by Hyosung is the commitment of such individual company only.

# POKETONE Injection Processing Guide



## Setting Temperature

- Recommended melting temperature: 235-250°C (460-490°F)
- Do not exceed 265°C (509°F). Long residence times at high end of the temperature range can cause thermal degradation & loss of physical properties.
- Mold Temperature: regarding POKETONE base grade, recommended setting temperature is at 60-80°C. In case of POKETONE glass-fiber reinforced grades, the temperature should be higher at least over 120°C for better surface quality.

## Cleaning Guide

- Please immediately clean barrels thoroughly after producing POKETONE products. Recommend high viscosity HDPE, PCTG and PP (Hyosung R200P). Other commercial purging compounds are also available.

## Drying

- Recommend drying POKETONE pellet at 80°C for about 3~4 hours. POKETONE should be dried by an oven or hopper drier to prevent surface problem like silver streak, drooling or voids.
- If the drying temperature is too high or the drying time is too long, it would be able to bring about discoloration of pellets.

If you need any further technical information, please contact our sales or marketing team who will be happy to assist you with any questions you may have. Feel free to visit our website. [www.poly-ketone.com](http://www.poly-ketone.com)