

Model M33AA2Y

File Number: E163907



COMPANY

Hyosung Chemical Corp
235, Banpo-daero, Seocho-gu
Seoul, Seoul 06578 Republic of Korea

MODEL INFO

M33AA2Y
Polyketone (PK), furnished as pellets

FLAMMABILITY PROPERTIES	VALUE	TEST METHOD
Flammability		ANSI/UL 94
0.8 mm, Color: ALL	V-0	
3.0 mm, Color: ALL	V-0	
ISO/IEC FLAMMABILITY PROPERTIES	VALUE	TEST METHOD
Flammability		IEC 60695-11-10
0.8 mm, Color: ALL	V-0	
3.0 mm, Color: ALL	V-0	
THERMAL PROPERTIES	VALUE	TEST METHOD
Relative Thermal Index - Electrical Strength		UL 746B
0.8 mm	50 °C	
3.0 mm	50 °C	
Relative Thermal Index - Mechanical Impact		UL 746B
0.8 mm	50 °C	
3.0 mm	50 °C	

Relative Thermal Index - Mechanical Strength		UL 746B
0.8 mm	50 °C	
3.0 mm	50 °C	

Report Date: 2022-01-17

Revision Date: 2022-01-17

The appearance of a company's name or product in this database does not in itself assure that products so identified have been manufactured under UL Solutions' Follow - Up Service. Only those products bearing the UL Mark should be considered to be Certified and covered under UL Solutions' Follow - Up Service. Always look for the Mark on the product.

UL Solutions permits the reproduction of the material contained in Product iQ subject to the following conditions: 1. The Guide Information, Assemblies, Constructions, Designs, Systems, and/or Certifications (files) must be presented in their entirety and in a non-misleading manner, without any manipulation of the data (or drawings). 2. The statement "Reprinted from Product iQ with permission from UL Solutions" must appear adjacent to the extracted material. In addition, the reprinted material must include a copyright notice in the following format: "©2023 UL LLC."