

Model M33(c)AG2J(#), M33AG2Y(e), M33AG2F(e), M33AG2P(e)

File Number: E163907



COMPANY

Hyosung Chemical Corp
235, Banpo-daero, Seocho-gu
Seoul, Seoul 06578 Republic of Korea

MODEL INFO

M33(c)AG2J(#), M33AG2Y(e), M33AG2F(e), M33AG2P(e)
Polyketone (PK), furnished as pellets
(e) – May be replaced by 1-2 letter(s) and 1-3 digit number(s).(coloring code)
(c) – Represents 1 digit numeric 0-9 which varies based on colors.
(#) – May be replaced by one letter (A-Z).

FLAMMABILITY PROPERTIES	VALUE	TEST METHOD
Flammability		ANSI/UL 94
0.8 mm, Color: ALL	V-0	
1.0 mm, Color: ALL	V-0	
1.6 mm, Color: ALL	V-0	
2.0 mm, Color: ALL	V-0	
3.0 mm, Color: ALL	V-0	
3.2 mm, Color: ALL	V-0	
ISO/IEC FLAMMABILITY PROPERTIES	VALUE	TEST METHOD
Flammability		IEC 60695-11-10
0.8 mm, Color: ALL	V-0	
1.0 mm, Color: ALL	V-0	
1.6 mm, Color: ALL	V-0	
2.0 mm, Color: ALL	V-0	
3.0 mm, Color: ALL	V-0	

3.2 mm, Color: ALL	V-0	
Glow Wire Ignition Temperature (GWIT)		IEC 60695-2-13
0.8 mm	825 °C	
1.0 mm	825 °C	
2.0 mm	825 °C	
3.0 mm	850 °C	
Glow Wire Flammability Index (GWFI)		IEC 60695-2-12
0.8 mm	960 °C	
1.0 mm	960 °C	
2.0 mm	960 °C	
3.0 mm	960 °C	
ELECTRICAL PROPERTIES	VALUE	TEST METHOD
Hot-wire Ignition (HWI)		UL 746A
0.8 mm	PLC 1	
1.0 mm	PLC 1	
1.6 mm	PLC 0	
2.0 mm	PLC 0	
3.0 mm	PLC 0	
3.2 mm	PLC 0	
High Amp Arc Ignition (HAI)		UL 746A
0.8 mm	PLC 0	
1.0 mm	PLC 0	
1.6 mm	PLC 0	
2.0 mm	PLC 0	
3.0 mm	PLC 0	
3.2 mm	PLC 0	
Comparative Tracking Index (CTI)	PLC 0	UL 746A
Dielectric Strength	29 kV/mm	ASTM D149
High Voltage Arc Tracking Rate (HVTR)	PLC 2	

Volume Resistivity	1.0E+12 ohms-cm	ASTM D257/IEC 60093
High Voltage, Low Current Arc Resistance	PLC 5	
THERMAL PROPERTIES	VALUE	TEST METHOD
Relative Thermal Index - Electrical Strength		UL 746B
0.8 mm	50 °C	
1.0 mm	50 °C	
1.6 mm	50 °C	
2.0 mm	50 °C	
3.0 mm	50 °C	
3.2 mm	50 °C	
Relative Thermal Index - Mechanical Impact		UL 746B
0.8 mm	50 °C	
1.0 mm	50 °C	
1.6 mm	50 °C	
2.0 mm	50 °C	
3.0 mm	50 °C	
3.2 mm	50 °C	
Relative Thermal Index - Mechanical Strength		UL 746B
0.8 mm	50 °C	
1.0 mm	50 °C	
1.6 mm	50 °C	
2.0 mm	50 °C	
3.0 mm	50 °C	
3.2 mm	50 °C	
Ball Pressure Temperature	155 °C	

The appearance of a company's name or product in this database does not in itself assure that products so identified have been manufactured under UL Solutions' Follow - Up Service. Only those products bearing the UL Mark should be considered to be Certified and covered under UL Solutions' Follow - Up Service. Always look for the Mark on the product.

UL Solutions permits the reproduction of the material contained in Product iQ subject to the following conditions: 1. The Guide Information, Assemblies, Constructions, Designs, Systems, and/or Certifications (files) must be presented in their entirety and in a non-misleading manner, without any manipulation of the data (or drawings). 2. The statement "Reprinted from Product iQ with permission from UL Solutions" must appear adjacent to the extracted material. In addition, the reprinted material must include a copyright notice in the following format: "©2023 UL LLC."