

POKETONE[®] E700

General

Feature	Barrier film grade for EVOH Blend
Special Characteristics	Excellent OTR
Processing method	Extrusion
Certification	EU No.10/2011
Colors available	Natural
UL File number	-
Form	Pellet
Applications	Film

Physical Properties

	ASTM	Value	ISO	Value
Density	D792	1.18 g/cm ³	1183	1.18 g/cm ³
Shore D hardness	D2240		868	
Hardness Rockwell	D785		2039	
Water absorption equilibrium at RH 50%	D570		62	
Water absorption at Saturation	D570		62	
Melt flow index 220°C/2.16kg	D1238	6 g/10 min	1133	
	D955		294-4	
Mold Shrinkage	MD, 3 mm			
	TD, 3 mm			
	MD, 2 mm			
	TD, 2 mm			

Mechanical Properties

	ASTM	Value	ISO	Value
Tensile strength at yield	D638	37 MPa	527-1	
Tensile modulus	D638		527-1	
Tensile elongation at yield	D638		527-1	
Tensile elongation at break	D638	150 %	527-1	
Flexural strength	D790	33 MPa	178	
Flexural modulus	D790	700 MPa	178	
Unnotched Izod impact strength	D256		180/1U	
Notched Izod impact strength	D256		180/1A	
Unnotched Charpy impact strength	D6110		179/1eU	

Notched Charpy impact strength	D6110	179/1eA	27 kJ/m ²
Falling dart impact strength		6603-2	

Thermal Properties

	ASTM	Value	ISO	Value
Melting temperature	D3418	197 °C	11357	197 °C
Coefficient of linear thermal expansion	E831		11359	
	25 ~ 55°C			
Vicat softening point	D1525		306/B50	
	5 kg		50 N	
Heat deflection temperature	D648		75	
	66 psi		0.45 MPa	
	264 psi		1.8 MPa	

Extrusion Processing Conditions

	Value
Drying temperature	80 °C
Drying time	3 ~ 4 hr
Suggested max moisture	0.20 %
Adapter & Die temperature	210 °C
Zone 5 temperature	210 °C
Zone 4 temperature	210 °C
Zone 3 temperature	215 °C
Zone 2 temperature	225 °C
Zone 1 temperature	230 °C
Jacket temperature	< 50 °C
Processing temperature	210 ~ 230 °C
L/D	> 26
Compression ratio	2.5 ~ 3.0

* The data listed here is not for specification warranty, but typical value.

All products purchased from or supplied by Hyosung Chemical Corporation are subject to terms and conditions set out in the contract, order acknowledgement and/or bill of loading. Values given above are simply references for representing typical level and do not expressly or impliedly guarantee anything. Neither should it be interpreted as specification limit nor sole criterion for part/tool design that is intended to have a legal binding effect. All other information, including that herein, supplied by Hyosung Chemical is considered accurate but is furnished upon the express condition that the customer shall make its own assessment to determine the product's suitability for a particular purpose. Hyosung Chemical makes no other warranty, either express or implied, including those regarding such other information, the data upon which the same is based, or the results to be obtained from the use thereof; that any product shall be merchantable or fit for any particular purpose; or that the use of such other information or product will not infringe any patent. Any references in this brochure to "Hyosung Chemical" refer to the collectivity of Hyosung Chemical engaged in the manufacture and sale of chemical products. Particular contracts are entered into by any such company individually and any warranty, representation or any other commitment provided by Hyosung Chemical is the commitment of such individual company only.