

POKETONE® M710F

General

Feature	Food & drug extrusion grade
Special Characteristics	Non-toxic, Low GWP
Processing method	Extrusion/injection
Certification	FDA, KFDA, EU No.10/2011, GMC Resolution 02/12 & 32/07, WRAS, USP Class VI, ISO 10993, EN71-Part3, RoHs, Free of PAHs, Free of Halogen, SVHC
Colors available	Natural
UL File number	-
Form	Pellet
Applications	Packaging Film, Coextrusion pipes, Blown film

Physical Properties

	ASTM	Value	ISO	Value
Density	D792	1.22 g/cm ³	1183	1.22 g/cm ³
Shore D hardness	D2240		868	75
Hardness Rockwell	D785	105	2039	
Water absorption equilibrium at RH 50%	D570	0.5 %	62	0.5 %
Water absorption at Saturation	D570	2.2 %	62	2.2 %
Melt flow index 220°C/2.16kg	D1238	3 g/10 min	1133	2.8 ml/10 min
Mold Shrinkage	D955		294-4	
	MD, 3 mm	1.7 %		
	TD, 3 mm	1.7 %		
	MD, 2 mm			
	TD, 2 mm			

Mechanical Properties

	ASTM	Value	ISO	Value
Tensile strength at yield	D638	43 MPa	527-1	43 MPa
Tensile modulus	D638	950 MPa	527-1	900 MPa
Tensile elongation at yield	D638	19 %	527-1	19 %
Tensile elongation at break	D638	≥ 200 %	527-1	≥ 200 %
Flexural strength	D790	40 MPa	178	40 MPa
Flexural modulus	D790	900 MPa	178	850 MPa
Unnotched Izod impact strength	D256	N.B.	180/1U	N.B.

Notched Izod impact strength	D256		180/1A	
	23 °C	200 J/m	23 °C	15 kJ/m ²
	-30 °C	50 J/m	-30 °C	4 kJ/m ²
Unnotched Charpy impact strength	D6110		179/1eU	N.B.
Notched Charpy impact strength	D6110		179/1eA	
			23 °C	14 kJ/m ²
			-30 °C	3 kJ/m ²
Falling dart impact strength			6603-2	

Thermal Properties

	ASTM	Value	ISO	Value
Melting temperature	D3418	197 °C	11357	197 °C
Coefficient of linear thermal expansion	E831 25 ~ 55°C	1.0×10 ⁻⁴	11359	
Vicat softening point	D1525 5 kg	155 °C	306/B50 50 N	152 °C
Heat deflection temperature	D648		75	
	66 psi	155 °C	0.45 MPa	140 °C
	264 psi	75 °C	1.8 MPa	65 °C

Flammability Properties

	Test Method & Condition	Value
Flame resistance	UL 94	HB (0.8 mm)

Electrical Properties

	Test Method & Condition	Value
Dielectric Strength (DS)	ASTM D149	
	3 mm	15 kV/mm
	2 mm	19 kV/mm
Volume Resistivity (VR)	ASTM D257	10 ¹⁴ Ω-cm
Surface Resistivity (SR)	ASTM D257	10 ¹⁷ Ω /m ²
Dielectric constant at 60Hz	ASTM D150	6.4
Dissipation factor at 60Hz	ASTM D150	0.014

Extrusion Processing Conditions

	Value
Pre-drying	Drying temperature
	80 °C
	Drying time
	3 ~ 4 hr

Temperature	Suggested max moisture	0.20 %
	Adapter & Die temperature	210 °C
	Zone 5 temperature	210 °C
	Zone 4 temperature	210 °C
	Zone 3 temperature	215 °C
	Zone 2 temperature	225 °C
	Zone 1 temperature	230 °C
	Jacket temperature	< 50 °C
	Processing temperature	210 ~ 230 °C
Screw Design	L/D	> 26
	Compression ratio	2.5 ~ 3.0

* The data listed here is not for specification warranty, but typical value.

All products purchased from or supplied by Hyosung Chemical Corporation are subject to terms and conditions set out in the contract, order acknowledgement and/or bill of loading. Values given above are simply references for representing typical level and do not expressly or impliedly guarantee anything. Neither should it be interpreted as specification limit nor sole criterion for part/tool design that is intended to have a legal binding effect. All other information, including that herein, supplied by Hyosung Chemical is considered accurate but is furnished upon the express condition that the customer shall make its own assessment to determine the product's suitability for a particular purpose. Hyosung Chemical makes no other warranty, either express or implied, including those regarding such other information, the data upon which the same is based, or the results to be obtained from the use thereof; that any product shall be merchantable or fit for any particular purpose; or that the use of such other information or product will not infringe any patent. Any references in this brochure to "Hyosung Chemical" refer to the collectivity of Hyosung Chemical engaged in the manufacture and sale of chemical products. Particular contracts are entered into by any such company individually and any warranty, representation or any other commitment provided by Hyosung Chemical is the commitment of such individual company only.